



DESCRIPTION

Chemguard AK1225 ZP High performance oil modified alkyd primers with selected functional rust inhibitive pigmentation. Available in a choice of six colors depending on the type of pigmentation. Offers easy workability, good adhesion and excellent corrosion protection.

Does not contain lead

RECOMMENDED USE

For the protection of steel surfaces in the field or shop, such as ironmongery, structural steel, tank exteriors, machinery, equipment, pipe exteriors, pipe racks, bar joists and other ferrous surfaces not exposed to severe chemical attack. Not recommended for immersion services, exposure to acids, alkalis or strong solvents.

SURFACE PREPARATION

Surfaces must be clean and sound. Employ adequate methods to remove dirt, dust, oil and all other contaminants that could interfere with adhesion.

Remove any oil or grease from surface to be coated with clean rags soaked in UNICHEM White Spirit or UNICHEM / Thinner #20. Allow surface to dry before application. For maximum performance, abrasive blast to a Commercial Finish in accordance with SSPC-SP6 to obtain a profile of 25 μ . Hand tool cleaning in accordance with SSPC-SP2 is acceptable.

MIXING

Power mix until uniform consistency. Avoid excessive air entrapment.

THINNING

Thin with no more than 1/2 liter of White Spirit per gallon for brush or roller application and no more than 1 liter for spray. Stir well before use.

APPLICATION

Apply by brush, roller or spray. Natural bristle brushes are preferred. Short-nap synthetic roller cover with phenolic core gives the best results for wide areas. Consult Unichem Technical Support Department for spray equipment instructions.

TECHNICAL INFORMATION

Color	Grey and White (Zinc Phosphate)
Viscosity	90 \pm 2 Kneb Units
Flash Point	Above 37°C
% Solids (by weight)	72% \pm 2
% Solids (by volume)	53% \pm 2
Density	1.30Kg/L
Dry Film Thickness	30-50 μ
Temperature Resistance	95°C
Drying Time	
Dry-to-touch	3 hours
Dry-to-recoat	18 hours
Full Cure Time	7 days
	* at 24°C and 50% RH

APPLICATION CONDITIONS

Min. Temperature 2°C

Max. Temperature 45°C

Relative Humidity 90%

THEORETICAL COVERAGE

10.6m²/L at 50μ

SHELF LIFE

12 months when stored properly in unopened container in dry conditions at 10 - 25°C.

CLEANUP

Tools and equipment can be cleaned with Thinner #10.

PACKAGING

Chemguard AK1210QD is available in 3.6 and 18 Liter .

PRECAUTIONS

KEEP OUT OF REACH OF CHILDREN. Use with adequate ventilation and use a respirator when levels are above applicable limits.

Avoid contact with skin and eyes. Close container after each use. Use good hygiene when handling this product.

TECHNICAL SUPPORT

Technical assistance is available from the manufacturers trained field representatives.

UPDATED

October 2017

Unichem Product Group

Unichem offers a wide range of industrial coatings, fireproofing and construction chemicals products that are manufactured, which include:

- Intumescent coatings
- Fire retardants
- Industrial floorings.
- Steel and industrial coatings
- Waterproofing.
- Grouts and anchoring
- Concrete repairs.
- Structural protection.